

562-80



PF 562 C (1008504)

Product description	S/A SURFACE PROTECTION FILM
Application	Surface protection film 562-80 is recommended for the protection of sensitive surfaces against dirt and damage during processing, storage and mounting e. g.: <ul style="list-style-type: none"> - smooth or slightly structured metallic surfaces - PVC-shapes (e. g. window-frames) - varnished surfaces - powder coated metallic surfaces - highgrade steel, brushed - Aluminium, polished or brushed

Technical data

Carrier	Polyethylene
Carrier colour	black / white
Total thickness [mm]	0,080
Application temperature °C	from 10°C to 40°C
Adhesive (inner side)	Rubber
Adhesion (inner side)	1,3 N/cm; +/- 04; QMP02 (internal method)
Resistance to oil	moderate
Resistance to solvents	moderate
UV resistance	600h QUV-Test*
Breaking strength Machine	>= 17 N/mm2 QMP03 (internal method)
Direction (MD)	
Breaking strength Transverse	> = 11 N/mm2
Direction (TD)	
Elongation at break Machine	>180 %
Direction (MD)	
Elongation at break Transverse	>380 %
Direction (TD)	
Storage	At room temperature 10 °C to 40 °C. For max. time of 6 months after production date.
Notes on application	Film covered products can be stored in moist conditions. Film must be removed from the product not later than given UV resistance period. Film should be removed at temperatures above +10 °C
	*600h corresponds to 6 months of external use in conditions Wipperfuert/Wesern Europe. Above data tolerance can be up to 15%.

Surface must be free from oil, fat, dust and solvents before film/tape application. Do not use cleaners containing anti-adhesive agents. Some plastics and paints may discharge anti-adhesive agents leading to bonding failure. Rough and uneven surfaces may weaken bonding. Product should be stored in original packaging, laid flat on the slit edge of the roll. Storage in dry and clean areas, at normal temperature, protected from direct sunlight and heat sources.

Statements, technical information and recommendation contained herein are based on tests we believe to be reliable but they are not to be construed in any manner as warranties expressed or implied. The user shall determine the suitability of the product for his intended use and assumes all risk and liability whatsoever in connection therewith.